

Species Adjustment Tables

Pages 2 - 25

& Specific Gravity vs. Moisture Content Table

Pages 26 - 31

for Wagner Models L606 and L607



WAGNER
ELECTRONICS

1-800-944-7078

Hardwood Species Adjustment Table

%Moisture Content

SG	Meter Reads ==>	5.0	6.0	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0
0.41	<i>Alder, Red</i>	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5
0.61	<i>Apple</i>	3.5	4.5	5.5	6.0	7.0	8.0	9.0	9.5	10.5	11.5
0.49	<i>Ash, Black</i>	6.0	7.0	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5
0.58	<i>Ash, Blue</i>	4.0	5.0	6.0	7.0	7.5	8.5	9.5	10.5	11.0	12.0
0.56	<i>Ash, Green</i>	4.5	5.5	6.5	7.0	8.0	9.0	10.0	11.0	11.5	12.5
0.55	<i>Ash, Oregon</i>	4.5	5.5	6.5	7.5	8.5	9.0	10.0	11.0	12.0	13.0
0.60	<i>Ash, White</i>	3.5	4.5	5.5	6.5	7.5	8.0	9.0	10.0	11.0	11.5
0.39	<i>Aspen, Bigtooth</i>	7.5	8.5	9.5	10.5	12.0	13.0	14.0	15.0	16.0	17.0
0.38	<i>Aspen, Quaking</i>	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.0	17.0
0.37	<i>Basswood, American</i>	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.5	17.5
0.64	<i>Beech, American</i>	3.0	4.0	4.5	5.5	6.5	7.0	8.0	9.0	10.0	10.5
0.55	<i>Birch, Paper</i>	4.5	5.5	6.5	7.5	8.5	9.0	10.0	11.0	12.0	13.0
0.65	<i>Birch, Sweet</i>	3.0	3.5	4.5	5.5	6.0	7.0	8.0	8.5	9.5	10.5
0.62	<i>Birch, Yellow</i>	3.5	4.0	5.0	6.0	7.0	7.5	8.5	9.5	10.5	11.0
0.38	<i>Butternut</i>	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.0	17.0

15.0	16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0
17.5	18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.0	27.0	28.0	29.0	30.0	31.0	32.0
12.5	13.0	14.0	15.0	15.5	16.5	17.5	18.5	19.0	20.0	21.0	22.0	22.5	23.5	24.5	25.5
15.5	16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	24.0	24.5	25.5	26.5	27.5	28.5	29.5
13.0	14.0	15.0	15.5	16.5	17.5	18.5	19.0	20.0	21.0	22.0	23.0	23.5	24.5	25.5	26.5
13.5	14.5	15.5	16.0	17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.5	24.5	25.0	26.0	27.0
14.0	14.5	15.5	16.5	17.5	18.5	19.0	20.0	21.0	22.0	23.0	24.0	24.5	25.5	26.5	27.5
12.5	13.5	14.5	15.0	16.0	17.0	18.0	18.5	19.5	20.5	21.5	22.0	23.0	24.0	25.0	25.5
18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.0
18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.5
18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5	31.5	32.5	33.5
11.5	12.5	13.0	14.0	15.0	16.0	16.5	17.5	18.5	19.0	20.0	21.0	21.5	22.5	23.5	24.5
14.0	14.5	15.5	16.5	17.5	18.5	19.0	20.0	21.0	22.0	23.0	24.0	24.5	25.5	26.5	27.5
11.5	12.0	13.0	14.0	14.5	15.5	16.5	17.0	18.0	19.0	19.5	20.5	21.5	22.5	23.0	24.0
12.0	13.0	13.5	14.5	15.5	16.5	17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.0	24.0	25.0
18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.5

Hardwood Species Adjustment Table cont'd

SG	Meter Reads ==>	%Moisture Content										
		5.0	6.0	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	
0.50	<i>Cherry, Black</i>	5.5	6.5	7.5	8.5	9.5	10.5	11.5	12.0	13.0	14.0	
0.43	<i>Chestnut, American</i>	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.0	
0.34	<i>Cottonwood, Balsam poplar</i>	8.5	9.5	11.0	12.0	13.0	14.0	15.0	16.0	17.0	18.0	
0.35	<i>Cottonwood, Black</i>	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	18.0	
0.40	<i>Cottonwood, Eastern</i>	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	
0.64	<i>Dogwood, Flowering</i>	3.0	4.0	4.5	5.5	6.5	7.0	8.0	9.0	10.0	10.5	
0.50	<i>Elm, American</i>	5.5	6.5	7.5	8.5	9.5	10.5	11.5	12.0	13.0	14.0	
0.63	<i>Elm, Rock</i>	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0	
0.53	<i>Elm, Slippery</i>	5.0	6.0	7.0	8.0	9.0	9.5	10.5	11.5	12.5	13.5	
0.53	<i>Hackberry</i>	5.0	6.0	7.0	8.0	9.0	9.5	10.5	11.5	12.5	13.5	
0.66	<i>Hickory (Pecan), Bitternut</i>	2.5	3.5	4.5	5.0	6.0	7.0	7.5	8.5	9.5	10.0	
0.60	<i>Hickory (Pecan), Nutmeg</i>	3.5	4.5	5.5	6.5	7.5	8.0	9.0	10.0	11.0	11.5	
0.66	<i>Hickory, Pecan</i>	2.5	3.5	4.5	5.0	6.0	7.0	7.5	8.5	9.5	10.0	
0.62	<i>Hickory (Pecan), Water</i>	3.5	4.0	5.0	6.0	7.0	7.5	8.5	9.5	10.5	11.0	
0.72	<i>Hickory (True), Mockernut</i>	1.5	2.5	3.0	4.0	4.5	5.5	6.5	7.0	8.0	8.5	

15.0	16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0
15.0	16.0	17.0	18.0	19.0	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.0	28.0	29.0
17.0	18.0	19.0	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5	31.5
19.0	20.0	21.0	22.0	23.0	24.0	25.5	26.5	27.5	28.5	29.5	30.5	31.5	32.5	33.5	34.5
19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.5	34.5
17.5	18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5	31.5	32.5
11.5	12.5	13.0	14.0	15.0	16.0	16.5	17.5	18.5	19.0	20.0	21.0	21.5	22.5	23.5	24.5
15.0	16.0	17.0	18.0	19.0	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.0	28.0	29.0
12.0	12.5	13.5	14.5	15.0	16.0	17.0	18.0	18.5	19.5	20.5	21.0	22.0	23.0	24.0	24.5
14.5	15.0	16.0	17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.5	24.5	25.5	26.0	27.0	28.0
14.5	15.0	16.0	17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.5	24.5	25.5	26.0	27.0	28.0
11.0	12.0	12.5	13.5	14.5	15.0	16.0	17.0	17.5	18.5	19.5	20.0	21.0	22.0	23.0	23.5
12.5	13.5	14.5	15.0	16.0	17.0	18.0	18.5	19.5	20.5	21.5	22.0	23.0	24.0	25.0	25.5
11.0	12.0	12.5	13.5	14.5	15.0	16.0	17.0	17.5	18.5	19.5	20.0	21.0	22.0	23.0	23.5
12.0	13.0	13.5	14.5	15.5	16.5	17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.0	24.0	25.0
9.5	10.5	11.0	12.0	12.5	13.5	14.5	15.0	16.0	16.5	17.5	18.5	19.0	20.0	20.5	21.5

Hardwood Species Adjustment Table cont'd

SG	Meter Reads ==>	%Moisture Content									
		5.0	6.0	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0
0.75	<i>Hickory (True), Pignut</i>	1.0	1.5	2.5	3.0	4.0	5.0	5.5	6.5	7.0	8.0
0.72	<i>Hickory (True), Shagbark</i>	1.5	2.5	3.0	4.0	4.5	5.5	6.5	7.0	8.0	8.5
0.69	<i>Hickory (True), Shellbark</i>	2.0	3.0	3.5	4.5	5.5	6.0	7.0	8.0	8.5	9.5
0.50	<i>Holly, American</i>	5.5	6.5	7.5	8.5	9.5	10.5	11.5	12.0	13.0	14.0
0.63	<i>Hophornbeam, Eastern</i>	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0
0.51	<i>Laurel, California</i>	5.5	6.5	7.5	8.0	9.0	10.0	11.0	12.0	13.0	14.0
0.69	<i>Locust, Black</i>	2.0	3.0	3.5	4.5	5.5	6.0	7.0	8.0	8.5	9.5
0.58	<i>Madrone, Pacific</i>	4.0	5.0	6.0	7.0	7.5	8.5	9.5	10.5	11.0	12.0
0.50	<i>Magnolia, Southern</i>	5.5	6.5	7.5	8.5	9.5	10.5	11.5	12.0	13.0	14.0
0.48	<i>Maple, Bigleaf</i>	6.0	7.0	8.0	9.0	10.0	11.0	11.5	12.5	13.5	14.5
0.57	<i>Maple, Black</i>	4.5	5.0	6.0	7.0	8.0	9.0	9.5	10.5	11.5	12.5
0.66	<i>Maple, Hard</i>	2.5	3.5	4.5	5.0	6.0	7.0	7.5	8.5	9.5	10.0
0.54	<i>Maple, Red</i>	5.0	6.0	6.5	7.5	8.5	9.5	10.5	11.5	12.0	13.0
0.47	<i>Maple, Silver</i>	6.0	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0
0.51	<i>Maple, Soft</i>	5.5	6.5	7.5	8.0	9.0	10.0	11.0	12.0	13.0	14.0

15.0	16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0
8.5	9.5	10.5	11.0	12.0	12.5	13.5	14.0	15.0	16.0	16.5	17.5	18.0	19.0	19.5	20.5
9.5	10.5	11.0	12.0	12.5	13.5	14.5	15.0	16.0	16.5	17.5	18.5	19.0	20.0	20.5	21.5
10.0	11.0	12.0	12.5	13.5	14.5	15.0	16.0	17.0	17.5	18.5	19.5	20.0	21.0	21.5	22.5
15.0	16.0	17.0	18.0	19.0	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.0	28.0	29.0
12.0	12.5	13.5	14.5	15.0	16.0	17.0	18.0	18.5	19.5	20.5	21.0	22.0	23.0	24.0	24.5
15.0	15.5	16.5	17.5	18.5	19.5	20.5	21.5	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0
10.0	11.0	12.0	12.5	13.5	14.5	15.0	16.0	17.0	17.5	18.5	19.5	20.0	21.0	21.5	22.5
13.0	14.0	15.0	15.5	16.5	17.5	18.5	19.0	20.0	21.0	22.0	23.0	23.5	24.5	25.5	26.5
15.0	16.0	17.0	18.0	19.0	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.0	28.0	29.0
15.5	16.5	17.5	18.5	19.5	20.5	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0
13.5	14.0	15.0	16.0	17.0	17.5	18.5	19.5	20.5	21.5	22.0	23.0	24.0	25.0	26.0	26.5
11.0	12.0	12.5	13.5	14.5	15.0	16.0	17.0	17.5	18.5	19.5	20.0	21.0	22.0	23.0	23.5
14.0	15.0	16.0	17.0	17.5	18.5	19.5	20.5	21.5	22.5	23.0	24.0	25.0	26.0	27.0	27.5
16.0	16.5	17.5	18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.0	29.0	30.0
15.0	15.5	16.5	17.5	18.5	19.5	20.5	21.5	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0

Hardwood Species Adjustment Table cont'd

SG	Meter Reads ==>	%Moisture Content										
		5.0	6.0	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	
0.63	<i>Maple, Sugar</i>	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0	
0.61	<i>Oak (Red), Black</i>	3.5	4.5	5.5	6.0	7.0	8.0	9.0	9.5	10.5	11.5	
0.51	<i>Oak, California black</i>	5.5	6.5	7.5	8.0	9.0	10.0	11.0	12.0	13.0	14.0	
0.68	<i>Oak (Red), Cherrybark</i>	2.0	3.0	4.0	4.5	5.5	6.5	7.0	8.0	9.0	9.5	
0.63	<i>Oak (Red), Laurel</i>	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0	
0.63	<i>Oak (Red), Northern red</i>	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0	
0.63	<i>Oak (Red), Pin</i>	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0	
0.67	<i>Oak (Red), Scarlet</i>	2.5	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	
0.59	<i>Oak (Red), Southern red</i>	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0	12.0	
0.63	<i>Oak (Red), Water</i>	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0	
0.69	<i>Oak (Red), Willow</i>	2.0	3.0	3.5	4.5	5.5	6.0	7.0	8.0	8.5	9.5	
0.64	<i>Oak, Red (1).</i>	3.0	4.0	4.5	5.5	6.5	7.0	8.0	9.0	10.0	10.5	
0.64	<i>Oak (White), Bur</i>	3.0	4.0	4.5	5.5	6.5	7.0	8.0	9.0	10.0	10.5	
0.66	<i>Oak (White), Chestnut</i>	2.5	3.5	4.5	5.0	6.0	7.0	7.5	8.5	9.5	10.0	
0.63	<i>Oak (White), Overcup</i>	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0	

15.0	16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0
12.0	12.5	13.5	14.5	15.0	16.0	17.0	18.0	18.5	19.5	20.5	21.0	22.0	23.0	24.0	24.5
12.5	13.0	14.0	15.0	15.5	16.5	17.5	18.5	19.0	20.0	21.0	22.0	22.5	23.5	24.5	25.5
15.0	15.5	16.5	17.5	18.5	19.5	20.5	21.5	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0
10.5	11.5	12.0	13.0	14.0	14.5	15.5	16.5	17.0	18.0	19.0	19.5	20.5	21.5	22.0	23.0
12.0	12.5	13.5	14.5	15.0	16.0	17.0	18.0	18.5	19.5	20.5	21.0	22.0	23.0	24.0	24.5
12.0	12.5	13.5	14.5	15.0	16.0	17.0	18.0	18.5	19.5	20.5	21.0	22.0	23.0	24.0	24.5
12.0	12.5	13.5	14.5	15.0	16.0	17.0	18.0	18.5	19.5	20.5	21.0	22.0	23.0	24.0	24.5
11.0	11.5	12.5	13.5	14.0	15.0	16.0	16.5	17.5	18.5	19.0	20.0	21.0	21.5	22.5	23.5
13.0	13.5	14.5	15.5	16.5	17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.5	24.0	25.0	26.0
12.0	12.5	13.5	14.5	15.0	16.0	17.0	18.0	18.5	19.5	20.5	21.0	22.0	23.0	24.0	24.5
10.0	11.0	12.0	12.5	13.5	14.5	15.0	16.0	17.0	17.5	18.5	19.5	20.0	21.0	21.5	22.5
11.5	12.5	13.0	14.0	15.0	16.0	16.5	17.5	18.5	19.0	20.0	21.0	21.5	22.5	23.5	24.5
11.5	12.5	13.0	14.0	15.0	16.0	16.5	17.5	18.5	19.0	20.0	21.0	21.5	22.5	23.5	24.5
11.0	12.0	12.5	13.5	14.5	15.0	16.0	17.0	17.5	18.5	19.5	20.0	21.0	22.0	23.0	23.5
12.0	12.5	13.5	14.5	15.0	16.0	17.0	18.0	18.5	19.5	20.5	21.0	22.0	23.0	24.0	24.5

Hardwood Species Adjustment Table cont'd

SG	Meter Reads ==>	%Moisture Content										
		5.0	6.0	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	
0.67	<i>Oak (White), Post</i>	2.5	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	
0.67	<i>Oak (White), Swamp chestnut</i>	2.5	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	
0.72	<i>Oak (White), Swamp white</i>	1.5	2.5	3.0	4.0	4.5	5.5	6.5	7.0	8.0	8.5	
0.66	<i>Oak, White</i>	2.5	3.5	4.5	5.0	6.0	7.0	7.5	8.5	9.5	10.0	
0.64	<i>Persimmon, Common</i>	3.0	4.0	4.5	5.5	6.5	7.0	8.0	9.0	10.0	10.5	
0.46	<i>Sassafras</i>	6.5	7.5	8.5	9.5	10.5	11.0	12.0	13.0	14.0	15.0	
0.52	<i>Sweetgum</i>	5.5	6.0	7.0	8.0	9.0	10.0	11.0	11.5	12.5	13.5	
0.49	<i>Sycamore, American</i>	6.0	7.0	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	
0.58	<i>Tanoak</i>	4.0	5.0	6.0	7.0	7.5	8.5	9.5	10.5	11.0	12.0	
0.50	<i>Tupelo, Black</i>	5.5	6.5	7.5	8.5	9.5	10.5	11.5	12.0	13.0	14.0	
0.50	<i>Tupelo, Water</i>	5.5	6.5	7.5	8.5	9.5	10.5	11.5	12.0	13.0	14.0	
0.55	<i>Walnut, Black</i>	4.5	5.5	6.5	7.5	8.5	9.0	10.0	11.0	12.0	13.0	
0.39	<i>Willow, Black</i>	7.5	8.5	9.5	10.5	12.0	13.0	14.0	15.0	16.0	17.0	
0.42	<i>Yellow-poplar</i>	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.0	

15.0	16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0
11.0	11.5	12.5	13.5	14.0	15.0	16.0	16.5	17.5	18.5	19.0	20.0	21.0	21.5	22.5	23.5
11.0	11.5	12.5	13.5	14.0	15.0	16.0	16.5	17.5	18.5	19.0	20.0	21.0	21.5	22.5	23.5
9.5	10.5	11.0	12.0	12.5	13.5	14.5	15.0	16.0	16.5	17.5	18.5	19.0	20.0	20.5	21.5
11.0	12.0	12.5	13.5	14.5	15.0	16.0	17.0	17.5	18.5	19.5	20.0	21.0	22.0	23.0	23.5
11.5	12.5	13.0	14.0	15.0	16.0	16.5	17.5	18.5	19.0	20.0	21.0	21.5	22.5	23.5	24.5
16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5
14.5	15.5	16.5	17.5	18.0	19.0	20.0	21.0	22.0	23.0	24.0	24.5	25.5	26.5	27.5	28.5
15.5	16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	24.0	24.5	25.5	26.5	27.5	28.5	29.5
13.0	14.0	15.0	15.5	16.5	17.5	18.5	19.0	20.0	21.0	22.0	23.0	23.5	24.5	25.5	26.5
15.0	16.0	17.0	18.0	19.0	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.0	28.0	29.0
15.0	16.0	17.0	18.0	19.0	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.0	28.0	29.0
14.0	14.5	15.5	16.5	17.5	18.5	19.0	20.0	21.0	22.0	23.0	24.0	24.5	25.5	26.5	27.5
18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.0
17.0	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0

Softwood Species Adjustment Table

SG	Meter Reads ==>	%Moisture Content										
		5.0	6.0	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	
0.46	<i>Baldcypress</i>	6.5	7.5	8.5	9.5	10.5	11.0	12.0	13.0	14.0	15.0	
0.44	<i>Cedar, Alaska</i>	7.0	8.0	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	
0.32	<i>Cedar, Atlantic white</i>	9.0	10.0	11.0	12.0	13.5	14.5	15.5	16.5	17.5	18.5	
0.47	<i>Cedar, Eastern red cedar</i>	6.0	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	
0.37	<i>Cedar, Incense</i>	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.5	17.5	
0.31	<i>Cedar, Northern white</i>	9.0	10.5	11.5	12.5	13.5	14.5	15.5	16.5	17.5	19.0	
0.43	<i>Cedar, Port Orford</i>	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.0	
0.32	<i>Cedar, Western red cedar</i>	9.0	10.0	11.0	12.0	13.5	14.5	15.5	16.5	17.5	18.5	
0.51	<i>Douglas fir</i>	5.0	6.0	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	
0.35	<i>Fir, Balsam</i>	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	18.0	
0.38	<i>Fir, California red</i>	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.0	17.0	
0.37	<i>Fir, Grand</i>	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.5	17.5	
0.39	<i>Fir, Noble</i>	7.5	8.5	9.5	10.5	12.0	13.0	14.0	15.0	16.0	17.0	
0.43	<i>Fir, Pacific silver</i>	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.0	
0.32	<i>Fir, Subalpine</i>	9.0	10.0	11.0	12.0	13.5	14.5	15.5	16.5	17.5	18.5	

15.0	16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0
16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5
16.5	17.5	18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.0	30.0	31.0
19.5	20.5	21.5	22.5	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.0	34.5	35.5
16.0	16.5	17.5	18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.0	29.0	30.0
18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5	31.5	32.5	33.5
20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.5	29.5	30.5	31.5	32.5	33.5	34.5	35.5
17.0	18.0	19.0	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5	31.5
19.5	20.5	21.5	22.5	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.0	34.5	35.5
15.0	16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0
19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.5	34.5
18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.5
18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5	31.5	32.5	33.5
18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.0
17.0	18.0	19.0	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5	31.5
19.5	20.5	21.5	22.5	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.0	34.5	35.5

Softwood Species Adjustment Table cont'd

SG	Meter Reads ==>	%Moisture Content									
		5.0	6.0	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0
0.39	<i>Fir, White</i>	7.5	8.5	9.5	10.5	12.0	13.0	14.0	15.0	16.0	17.0
0.40	<i>Hemlock, Eastern</i>	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5
0.45	<i>Hemlock, Mountain</i>	6.5	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5
0.45	<i>Hemlock, Western</i>	6.5	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5
0.52	<i>Larch, Western</i>	5.5	6.0	7.0	8.0	9.0	10.0	11.0	11.5	12.5	13.5
0.35	<i>Pine, Eastern white</i>	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	18.0
0.43	<i>Pine, Jack</i>	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.0
0.51	<i>Pine, Loblolly</i>	5.5	6.5	7.5	8.0	9.0	10.0	11.0	12.0	13.0	14.0
0.41	<i>Pine, Lodgepole</i>	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5
0.59	<i>Pine, Longleaf</i>	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0	12.0
0.52	<i>Pine, Pitch</i>	5.5	6.0	7.0	8.0	9.0	10.0	11.0	11.5	12.5	13.5
0.56	<i>Pine, Pond</i>	4.5	5.5	6.5	7.0	8.0	9.0	10.0	11.0	11.5	12.5
0.40	<i>Pine, Ponderosa</i>	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5
0.46	<i>Pine, Red</i>	6.5	7.5	8.5	9.5	10.5	11.0	12.0	13.0	14.0	15.0
0.48	<i>Pine, Sand</i>	6.0	7.0	8.0	9.0	10.0	11.0	11.5	12.5	13.5	14.5

15.0	16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0
18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.0
17.5	18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5	31.5	32.5
16.5	17.5	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0
16.5	17.5	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0
14.5	15.5	16.5	17.5	18.0	19.0	20.0	21.0	22.0	23.0	24.0	24.5	25.5	26.5	27.5	28.5
19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.5	34.5
17.0	18.0	19.0	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5	31.5
15.0	15.5	16.5	17.5	18.5	19.5	20.5	21.5	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0
17.5	18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.0	27.0	28.0	29.0	30.0	31.0	32.0
13.0	13.5	14.5	15.5	16.5	17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.5	24.0	25.0	26.0
14.5	15.5	16.5	17.5	18.0	19.0	20.0	21.0	22.0	23.0	24.0	24.5	25.5	26.5	27.5	28.5
13.5	14.5	15.5	16.0	17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.5	24.5	25.0	26.0	27.0
17.5	18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5	31.5	32.5
16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5
15.5	16.5	17.5	18.5	19.5	20.5	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0

Softwood Species Adjustment Table cont'd

		%Moisture Content										
SG	Meter Reads ==>	5.0	6.0	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	
0.51	<i>Pine, Shortleaf</i>	5.5	6.5	7.5	8.0	9.0	10.0	11.0	12.0	13.0	14.0	
0.59	<i>Pine, Slash</i>	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0	12.0	
0.44	<i>Pine, Spruce</i>	7.0	8.0	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	
0.36	<i>Pine, Sugar</i>	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	17.5	
0.48	<i>Pine, Virginia</i>	6.0	7.0	8.0	9.0	10.0	11.0	11.5	12.5	13.5	14.5	
0.38	<i>Pine, Western white</i>	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.0	17.0	
0.40	<i>Redwood, Old-growth</i>	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	
0.35	<i>Redwood, Young-growth</i>	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	18.0	
0.42	<i>Spruce, Black</i>	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.0	
0.35	<i>Spruce, Engelmann</i>	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	18.0	
0.40	<i>Spruce, Red</i>	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	
0.40	<i>Spruce, Sitka</i>	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	
0.36	<i>Spruce, White</i>	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	17.5	
0.51	<i>SYP</i>	5.5	6.5	7.5	8.0	9.0	10.0	11.0	12.0	13.0	14.0	
0.53	<i>Tamarack</i>	5.0	6.0	7.0	8.0	9.0	9.5	10.5	11.5	12.5	13.5	

15.0	16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0
15.0	15.5	16.5	17.5	18.5	19.5	20.5	21.5	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0
13.0	13.5	14.5	15.5	16.5	17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.5	24.0	25.0	26.0
16.5	17.5	18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.0	30.0	31.0
18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	27.0	28.0	29.0	30.0	31.0	32.0	33.0	34.0
15.5	16.5	17.5	18.5	19.5	20.5	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0
18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.5
17.5	18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5	31.5	32.5
19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.5	34.5
17.0	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0
19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.5	34.5
17.5	18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5	31.5	32.5
17.5	18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5	31.5	32.5
18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	27.0	28.0	29.0	30.0	31.0	32.0	33.0	34.0
15.0	15.5	16.5	17.5	18.5	19.5	20.5	21.5	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0
14.5	15.0	16.0	17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.5	24.5	25.5	26.0	27.0	28.0

Imported Species Adjustment Table

SG	Meter Reads ==>	%Moisture Content										
		5.0	6.0	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	
0.69	<i>Afromosia</i>	2.0	3.0	3.5	4.5	5.5	6.0	7.0	8.0	8.5	9.5	
0.64	<i>Andiroba</i>	3.0	4.0	4.5	5.5	6.5	7.0	8.0	9.0	10.0	10.5	
0.54	<i>Anegre</i>	5.0	6.0	6.5	7.5	8.5	9.5	10.5	11.5	12.0	13.0	
0.55	<i>Avodire</i>	4.5	5.5	6.5	7.5	8.5	9.0	10.0	11.0	12.0	13.0	
0.62	<i>Banak (Cuangare)</i>	3.5	4.0	5.0	6.0	7.0	7.5	8.5	9.5	10.5	11.0	
0.77	<i>Benge (Ehie, Bubinga)</i>	0.5	1.5	2.5	3.0	4.0	4.5	5.5	6.0	7.0	7.5	
0.61	<i>Caribbean pine</i>	3.5	4.5	5.5	6.0	7.0	8.0	9.0	9.5	10.5	11.5	
0.44	<i>Cativo</i>	7.0	8.0	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	
0.51	<i>Cypress</i>	5.5	6.5	7.5	8.0	9.0	10.0	11.0	12.0	13.0	14.0	
0.82	<i>Degame</i>	0.0	0.5	1.0	2.0	2.5	3.5	4.0	5.0	5.5	6.0	
0.58	<i>Determa</i>	4.0	5.0	6.0	7.0	7.5	8.5	9.5	10.5	11.0	12.0	
0.70	<i>Ebony, East Indian</i>	2.0	2.5	3.5	4.5	5.0	6.0	6.5	7.5	8.5	9.0	
0.50	<i>Gmelina</i>	5.5	6.5	7.5	8.5	9.5	10.5	11.5	12.0	13.0	14.0	
0.38	<i>Hura</i>	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.0	17.0	
0.70	<i>Iroko</i>	2.0	2.5	3.5	4.5	5.0	6.0	6.5	7.5	8.5	9.0	

15.0	16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0
10.0	11.0	12.0	12.5	13.5	14.5	15.0	16.0	17.0	17.5	18.5	19.5	20.0	21.0	21.5	22.5
11.5	12.5	13.0	14.0	15.0	16.0	16.5	17.5	18.5	19.0	20.0	21.0	21.5	22.5	23.5	24.5
14.0	15.0	16.0	17.0	17.5	18.5	19.5	20.5	21.5	22.5	23.0	24.0	25.0	26.0	27.0	27.5
14.0	14.5	15.5	16.5	17.5	18.5	19.0	20.0	21.0	22.0	23.0	24.0	24.5	25.5	26.5	27.5
12.0	13.0	13.5	14.5	15.5	16.5	17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.0	24.0	25.0
8.5	9.0	10.0	11.0	11.5	12.5	13.0	14.0	14.5	15.5	16.0	17.0	17.5	18.5	19.0	20.0
12.5	13.0	14.0	15.0	15.5	16.5	17.5	18.5	19.0	20.0	21.0	22.0	22.5	23.5	24.5	25.5
16.5	17.5	18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.0	30.0	31.0
15.0	15.5	16.5	17.5	18.5	19.5	20.5	21.5	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0
7.0	7.5	8.5	9.0	10.0	10.5	11.5	12.0	13.0	13.5	14.5	15.0	16.0	16.5	17.5	18.0
13.0	14.0	15.0	15.5	16.5	17.5	18.5	19.0	20.0	21.0	22.0	23.0	23.5	24.5	25.5	26.5
10.0	11.0	11.5	12.5	13.5	14.0	15.0	15.5	16.5	17.5	18.0	19.0	20.0	20.5	21.5	22.0
15.0	16.0	17.0	18.0	19.0	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.0	28.0	29.0
18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.5
10.0	11.0	11.5	12.5	13.5	14.0	15.0	15.5	16.5	17.5	18.0	19.0	20.0	20.5	21.5	22.0

Imported Species Adjustment Table cont'd

SG	Meter Reads ==>	%Moisture Content										
		5.0	6.0	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	
0.80	<i>Jarrah</i>	0.0	0.5	1.5	2.0	2.5	3.5	4.0	5.0	5.5	6.5	
0.46	<i>Jelutong</i>	6.5	7.5	8.5	9.5	10.5	11.0	12.0	13.0	14.0	15.0	
0.76	<i>Kapur</i>	0.5	1.5	2.5	3.0	4.0	4.5	5.5	6.0	7.0	7.5	
0.64	<i>Keruing (Apitong)</i>	3.0	4.0	4.5	5.5	6.5	7.0	8.0	9.0	10.0	10.5	
0.67	<i>Koa</i>	2.5	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	
0.67	<i>Lauan, Dark Red</i>	2.5	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	
0.50	<i>Lauan, White (Light Red Meranti)</i>	5.5	6.5	7.5	8.5	9.5	10.5	11.5	12.0	13.0	14.0	
0.45	<i>Limba</i>	6.5	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	
0.61	<i>Mahogany, African</i>	3.5	4.5	5.5	6.0	7.0	8.0	9.0	9.5	10.5	11.5	
0.59	<i>Mahogany, True</i>	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0	12.0	
0.68	<i>Manni</i>	2.0	3.0	4.0	4.5	5.5	6.5	7.0	8.0	9.0	9.5	
0.80	<i>Merbau</i>	0.0	0.5	1.5	2.0	2.5	3.5	4.0	5.0	5.5	6.5	
0.65	<i>Mersawa</i>	3.0	3.5	4.5	5.5	6.0	7.0	8.0	8.5	9.5	10.5	
0.63	<i>Mueri (Cherry)</i>	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0	
0.38	<i>Obeche</i>	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.0	17.0	

15.0	16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0
7.0	8.0	8.5	9.5	10.0	11.0	11.5	12.5	13.0	14.0	14.5	15.5	16.0	17.0	17.5	18.5
16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5
8.5	9.5	10.0	11.0	11.5	12.5	13.0	14.0	14.5	15.5	16.5	17.0	18.0	18.5	19.5	20.0
11.5	12.5	13.0	14.0	15.0	16.0	16.5	17.5	18.5	19.0	20.0	21.0	21.5	22.5	23.5	24.5
11.0	11.5	12.5	13.5	14.0	15.0	16.0	16.5	17.5	18.5	19.0	20.0	21.0	21.5	22.5	23.5
11.0	11.5	12.5	13.5	14.0	15.0	16.0	16.5	17.5	18.5	19.0	20.0	21.0	21.5	22.5	23.5
15.0	16.0	17.0	18.0	19.0	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.0	28.0	29.0
16.5	17.5	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0
12.5	13.0	14.0	15.0	15.5	16.5	17.5	18.5	19.0	20.0	21.0	22.0	22.5	23.5	24.5	25.5
13.0	13.5	14.5	15.5	16.5	17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.5	24.0	25.0	26.0
10.5	11.5	12.0	13.0	14.0	14.5	15.5	16.5	17.0	18.0	19.0	19.5	20.5	21.5	22.0	23.0
7.0	8.0	8.5	9.5	10.0	11.0	11.5	12.5	13.0	14.0	14.5	15.5	16.0	17.0	17.5	18.5
11.5	12.0	13.0	14.0	14.5	15.5	16.5	17.0	18.0	19.0	19.5	20.5	21.5	22.5	23.0	24.0
12.0	12.5	13.5	14.5	15.0	16.0	17.0	18.0	18.5	19.5	20.5	21.0	22.0	23.0	24.0	24.5
18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.5

Imported Species Adjustment Table cont'd

SG	Meter Reads ==>	%Moisture Content										
		5.0	6.0	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	
0.66	<i>Ocote pine</i>	2.5	3.5	4.5	5.0	6.0	7.0	7.5	8.5	9.5	10.0	
0.44	<i>Okoume</i>	7.0	8.0	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	
0.73	<i>Opepe</i>	1.5	2.0	3.0	3.5	4.5	5.5	6.0	7.0	7.5	8.5	
0.54	<i>Parana pine</i>	5.0	6.0	6.5	7.5	8.5	9.5	10.5	11.5	12.0	13.0	
0.63	<i>Peroba de campos</i>	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0	
0.75	<i>Peroba rosa</i>	1.0	1.5	2.5	3.0	4.0	5.0	5.5	6.5	7.0	8.0	
0.45	<i>Primavera</i>	6.5	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	
0.80	<i>Purpleheart</i>	0.0	0.5	1.5	2.0	2.5	3.5	4.0	5.0	5.5	6.5	
0.48	<i>Radiata pine</i>	6.0	7.0	8.0	9.0	10.0	11.0	11.5	12.5	13.5	14.5	
0.65	<i>Ramin</i>	3.0	3.5	4.5	5.5	6.0	7.0	8.0	8.5	9.5	10.5	
0.64	<i>Roble (Quercus)</i>	3.0	4.0	4.5	5.5	6.5	7.0	8.0	9.0	10.0	10.5	
0.85	<i>Rosewood, Brazilian (Jacaranda)</i>	0.0	0.0	0.5	1.0	2.0	2.5	3.5	4.0	5.0	5.5	
0.85	<i>Rosewood, Indian</i>	0.0	0.0	0.5	1.0	2.0	2.5	3.5	4.0	5.0	5.5	
0.61	<i>Santa Maria</i>	3.5	4.5	5.5	6.0	7.0	8.0	9.0	9.5	10.5	11.5	
0.62	<i>Sapele</i>	3.5	4.0	5.0	6.0	7.0	7.5	8.5	9.5	10.5	11.0	

15.0	16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0
11.0	12.0	12.5	13.5	14.5	15.0	16.0	17.0	17.5	18.5	19.5	20.0	21.0	22.0	23.0	23.5
16.5	17.5	18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.0	30.0	31.0
9.0	10.0	11.0	11.5	12.5	13.0	14.0	15.0	15.5	16.5	17.0	18.0	19.0	19.5	20.5	21.0
14.0	15.0	16.0	17.0	17.5	18.5	19.5	20.5	21.5	22.5	23.0	24.0	25.0	26.0	27.0	27.5
12.0	12.5	13.5	14.5	15.0	16.0	17.0	18.0	18.5	19.5	20.5	21.0	22.0	23.0	24.0	24.5
8.5	9.5	10.5	11.0	12.0	12.5	13.5	14.0	15.0	16.0	16.5	17.5	18.0	19.0	19.5	20.5
16.5	17.5	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0
7.0	8.0	8.5	9.5	10.0	11.0	11.5	12.5	13.0	14.0	14.5	15.5	16.0	17.0	17.5	18.5
15.5	16.5	17.5	18.5	19.5	20.5	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0
11.5	12.0	13.0	14.0	14.5	15.5	16.5	17.0	18.0	19.0	19.5	20.5	21.5	22.5	23.0	24.0
11.5	12.5	13.0	14.0	15.0	16.0	16.5	17.5	18.5	19.0	20.0	21.0	21.5	22.5	23.5	24.5
6.0	7.0	7.5	8.5	9.0	10.0	10.5	11.5	12.0	12.5	13.5	14.0	15.0	15.5	16.5	17.0
6.0	7.0	7.5	8.5	9.0	10.0	10.5	11.5	12.0	12.5	13.5	14.0	15.0	15.5	16.5	17.0
12.5	13.0	14.0	15.0	15.5	16.5	17.5	18.5	19.0	20.0	21.0	22.0	22.5	23.5	24.5	25.5
12.0	13.0	13.5	14.5	15.5	16.5	17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.0	24.0	25.0

Imported Species Adjustment Table cont'd

SG	Meter Reads ==>	%Moisture Content										
		5.0	6.0	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	
0.41	<i>Spanish Cedar</i>	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	
0.59	<i>Teak</i>	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0	12.0	
0.67	<i>Yew</i>	2.5	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	

Plywood and OSB Correction Factors

Southern Yellow Pine CDX Plywood (2).	Deduct 1% from Meter Reading
Douglas Fir CDX Plywood (2).	Deduct 1% from Meter Reading
Southern Yellow Pine OSB (2).	Deduct 4% from Meter Reading
Douglas Fir OSB (2).	Deduct 4% from Meter Reading

15.0	16.0	17.0	18.0	19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0
17.5	18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.0	27.0	28.0	29.0	30.0	31.0	32.0
13.0	13.5	14.5	15.5	16.5	17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.5	24.0	25.0	26.0
11.0	11.5	12.5	13.5	14.0	15.0	16.0	16.5	17.5	18.5	19.0	20.0	21.0	21.5	22.5	23.5

Specific Gravity Correction Value Sources

(1). This SG correction value was developed by Wagner Electronic Products ,Inc.

(2). This SG correction value was developed by Wagner Electronic Products, Inc.

The above numbers are based on our research and have been developed to give users a general correction factor for the above-mentioned plywoods & OSB. Please keep in mind that plywood & OSB manufacturing processes can differ slightly and some plywood and OSB of the same species may vary slightly. NOTE: The L607 is designed for use on finely sanded material.

Specific Gravity vs. Moisture Content

	%Moisture Content												
SG	5	6	7	8	9	10	11	12	13	14	15	16	17
0.30	9.5	10.5	11.5	12.5	13.5	14.5	16.0	17.0	18.0	19.0	20.0	21.0	22.0
0.31	9.0	10.5	11.5	12.5	13.5	14.5	15.5	16.5	17.5	19.0	20.0	21.0	22.0
0.32	9.0	10.0	11.0	12.0	13.5	14.5	15.5	16.5	17.5	18.5	19.5	20.5	21.5
0.33	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.0	17.0	18.5	19.5	20.5	21.5
0.34	8.5	9.5	11.0	12.0	13.0	14.0	15.0	16.0	17.0	18.0	19.0	20.0	21.0
0.35	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	18.0	19.0	20.0	21.0
0.36	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	17.5	18.5	19.5	20.5
0.37	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.5	17.5	18.5	19.5	20.5
0.38	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.0	17.0	18.0	19.0	20.0
0.39	7.5	8.5	9.5	10.5	12.0	13.0	14.0	15.0	16.0	17.0	18.0	19.0	20.0
0.40	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	17.5	18.5	19.5
0.41	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	17.5	18.5	19.5
0.42	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.0	17.0	18.0	19.0
0.43	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.0	17.0	18.0	19.0
0.44	7.0	8.0	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	17.5	18.5
0.45	6.5	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.5	17.5	18.0

18	19	20	21	22	23	24	25	26	27	28	29	30
23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5	32.0	33.0	34.0	35.0	36.0
23.0	24.0	25.0	26.0	27.0	28.5	29.5	30.5	31.5	32.5	33.5	34.5	35.5
22.5	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.0	34.5	35.5
22.5	23.5	24.5	25.5	26.5	27.5	28.5	30.0	31.0	32.0	33.0	34.0	35.0
22.0	23.0	24.0	25.5	26.5	27.5	28.5	29.5	30.5	31.5	32.5	33.5	34.5
22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.5	34.5
21.5	22.5	23.5	24.5	25.5	27.0	28.0	29.0	30.0	31.0	32.0	33.0	34.0
21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5	31.5	32.5	33.5
21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.5
21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0	33.0
20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5	31.5	32.5
20.5	21.5	22.5	23.5	24.5	25.5	26.0	27.0	28.0	29.0	30.0	31.0	32.0
20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0	32.0
19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5	31.5
19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.5	29.0	30.0	31.0
19.0	20.0	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0	31.0

Specific Gravity vs. Moisture Content cont'd

	%Moisture Content												
SG	5	6	7	8	9	10	11	12	13	14	15	16	17
0.46	6.5	7.5	8.5	9.5	10.5	11.0	12.0	13.0	14.0	15.0	16.0	17.0	18.0
0.47	6.0	7.0	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	16.0	16.5	17.5
0.48	6.0	7.0	8.0	9.0	10.0	11.0	11.5	12.5	13.5	14.5	15.5	16.5	17.5
0.49	6.0	7.0	7.5	8.5	9.5	10.5	11.5	12.5	13.5	14.5	15.5	16.0	17.0
0.50	5.5	6.5	7.5	8.5	9.5	10.5	11.5	12.0	13.0	14.0	15.0	16.0	17.0
0.51	5.5	6.5	7.5	8.0	9.0	10.0	11.0	12.0	13.0	14.0	15.0	15.5	16.5
0.52	5.5	6.0	7.0	8.0	9.0	10.0	11.0	11.5	12.5	13.5	14.5	15.5	16.5
0.53	5.0	6.0	7.0	8.0	9.0	9.5	10.5	11.5	12.5	13.5	14.5	15.0	16.0
0.54	5.0	6.0	6.5	7.5	8.5	9.5	10.5	11.5	12.0	13.0	14.0	15.0	16.0
0.55	4.5	5.5	6.5	7.5	8.5	9.0	10.0	11.0	12.0	13.0	14.0	14.5	15.5
0.56	4.5	5.5	6.5	7.0	8.0	9.0	10.0	11.0	11.5	12.5	13.5	14.5	15.5
0.57	4.5	5.0	6.0	7.0	8.0	9.0	9.5	10.5	11.5	12.5	13.5	14.0	15.0
0.58	4.0	5.0	6.0	7.0	7.5	8.5	9.5	10.5	11.0	12.0	13.0	14.0	15.0
0.59	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0	12.0	13.0	13.5	14.5
0.60	3.5	4.5	5.5	6.5	7.5	8.0	9.0	10.0	11.0	11.5	12.5	13.5	14.5
0.61	3.5	4.5	5.5	6.0	7.0	8.0	9.0	9.5	10.5	11.5	12.5	13.0	14.0

18	19	20	21	22	23	24	25	26	27	28	29	30
19.0	20.0	21.0	22.0	23.0	23.5	24.5	25.5	26.5	27.5	28.5	29.5	30.5
18.5	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.5	28.0	29.0	30.0
18.5	19.5	20.5	21.0	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0	30.0
18.0	19.0	20.0	21.0	22.0	23.0	24.0	24.5	25.5	26.5	27.5	28.5	29.5
18.0	19.0	19.5	20.5	21.5	22.5	23.5	24.5	25.5	26.5	27.0	28.0	29.0
17.5	18.5	19.5	20.5	21.5	22.0	23.0	24.0	25.0	26.0	27.0	28.0	29.0
17.5	18.0	19.0	20.0	21.0	22.0	23.0	24.0	24.5	25.5	26.5	27.5	28.5
17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.5	24.5	25.5	26.0	27.0	28.0
17.0	17.5	18.5	19.5	20.5	21.5	22.5	23.0	24.0	25.0	26.0	27.0	27.5
16.5	17.5	18.5	19.0	20.0	21.0	22.0	23.0	24.0	24.5	25.5	26.5	27.5
16.0	17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.5	24.5	25.0	26.0	27.0
16.0	17.0	17.5	18.5	19.5	20.5	21.5	22.0	23.0	24.0	25.0	26.0	26.5
15.5	16.5	17.5	18.5	19.0	20.0	21.0	22.0	23.0	23.5	24.5	25.5	26.5
15.5	16.5	17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.5	24.0	25.0	26.0
15.0	16.0	17.0	18.0	18.5	19.5	20.5	21.5	22.0	23.0	24.0	25.0	25.5
15.0	15.5	16.5	17.5	18.5	19.0	20.0	21.0	22.0	22.5	23.5	24.5	25.5

Specific Gravity vs. Moisture Content cont'd

	%Moisture Content												
SG	5	6	7	8	9	10	11	12	13	14	15	16	17
0.62	3.5	4.0	5.0	6.0	7.0	7.5	8.5	9.5	10.5	11.0	12.0	13.0	13.5
0.63	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0	12.0	12.5	13.5
0.64	3.0	4.0	4.5	5.5	6.5	7.0	8.0	9.0	10.0	10.5	11.5	12.5	13.0
0.65	3.0	3.5	4.5	5.5	6.0	7.0	8.0	8.5	9.5	10.5	11.5	12.0	13.0
0.66	2.5	3.5	4.5	5.0	6.0	7.0	7.5	8.5	9.5	10.0	11.0	12.0	12.5
0.67	2.5	3.0	4.0	5.0	5.5	6.5	7.5	8.5	9.0	10.0	11.0	11.5	12.5
0.68	2.0	3.0	4.0	4.5	5.5	6.5	7.0	8.0	9.0	9.5	10.5	11.5	12.0
0.69	2.0	3.0	3.5	4.5	5.5	6.0	7.0	8.0	8.5	9.5	10.0	11.0	12.0
0.70	2.0	2.5	3.5	4.5	5.0	6.0	6.5	7.5	8.5	9.0	10.0	11.0	11.5

18	19	20	21	22	23	24	25	26	27	28	29	30
14.5	15.5	16.5	17.0	18.0	19.0	20.0	20.5	21.5	22.5	23.0	24.0	25.0
14.5	15.0	16.0	17.0	18.0	18.5	19.5	20.5	21.0	22.0	23.0	24.0	24.5
14.0	15.0	16.0	16.5	17.5	18.5	19.0	20.0	21.0	21.5	22.5	23.5	24.5
14.0	14.5	15.5	16.5	17.0	18.0	19.0	19.5	20.5	21.5	22.5	23.0	24.0
13.5	14.5	15.0	16.0	17.0	17.5	18.5	19.5	20.0	21.0	22.0	23.0	23.5
13.5	14.0	15.0	16.0	16.5	17.5	18.5	19.0	20.0	21.0	21.5	22.5	23.5
13.0	14.0	14.5	15.5	16.5	17.0	18.0	19.0	19.5	20.5	21.5	22.0	23.0
12.5	13.5	14.5	15.0	16.0	17.0	17.5	18.5	19.5	20.0	21.0	21.5	22.5
12.5	13.5	14.0	15.0	15.5	16.5	17.5	18.0	19.0	20.0	20.5	21.5	22.0



Wagner Electronic Products, Inc.

326 Pine Grove Road, Rogue River, OR 97537 USA

Phone: (541) 582-0541, Fax: (541) 582-4138

E-mail: Sales@www.wagner.com

Visit us on the Web at:

<http://www.moisturemeters.com>

© 2004 WEPI Wagner Part No: 500-60601-003 Rev. N/C